

LAW OFFICES
ANTONELLI, TERRY, STOUT & KRAUS, LLP
SUITE 1800
1300 NORTH SEVENTEENTH STREET
ARLINGTON, VIRGINIA 22209

TELEPHONE: (703) 312-6600 FACSIMILE (703) 312-6666

FACSIMILE TRANSMISSION		
From: <u>William I. Solomon</u>	Date: <u>November 6, 2002</u>	
U.S. Serial No. Attorney Docket: 500.38665CX1	No. of Pages: <u>6</u>	(including cover sheet)
Deliver To	Facsimile Number	ATTACHMENTS
Examiner J. J. Zimmerman	703 872-9019	Proposed Amendments for discussion at interview this afternoon

Urgent For Review Please Comment Please Reply

COMMENTS/MESSAGE:

If you experience any problem regarding this transmission, please contact ext. 6647.

Confirmation Copy will not follow.

CONFIDENTIALITY NOTICE: The document accompanying this facsimile transmission contains confidential information belonging to the sender which is legally privileged. The information is intended only for the use of the individual(s) or entity(ies) named above. If you are not the intended recipient, you are hereby notified that any disclosure, copying, distribution or the taking of any action in reliance on the contents of this facsimile information is strictly prohibited. If you have received this facsimile in error, please immediately notify us by telephone to arrange for return of the original document to us.

Proposed New Claims A, B and C for Application No. 09/581,631 for discussion during
Interview on November 6, 2002

A. An electronic device comprising:

an electronic component having a first electrode; and
a second electrode formed on a circuit board, the first electrode and the second
electrode being electrically connected to each other, and bonded to each other with a
Pb-free solder, providing a connection between the first and second electrodes,
wherein the connection is made by contacting and soldering the Pb-free solder
with an electrode structure including the first electrode, the electrode structure
comprising the first electrode and a layered structure thereon consisting of an Sn-Bi
alloy layer containing 1-5 wt % Bi.

B. An electronic device comprising:

an electronic component having a first electrode; and
a second electrode provided on a circuit board on which the electronic
component is mounted, the first electrode and the second electrode being bonded to
each other by a Pb-free solder, providing a connection between the first and second
electrodes,
wherein the connection is made by contacting and soldering the Pb-free solder
with an electrode structure including the first electrode and a layered structure thereon
consisting of an Sn-Bi alloy layer containing 1-5 wt% Bi.

C. An electronic device comprising:
an electronic component having a first electrode; and
a second electrode formed on a circuit board, the first electrode and the second
electrode being electrically connected to each other, and bonded to each other with a
Pb-free solder, providing a connection between the first and second electrodes,
wherein the connection is made by contacting and soldering the Pb-free solder
with an electrode structure including the first electrode and a layered structure thereon
consisting of an Sn-Bi alloy layer containing 1-5 wt% Bi.

Proposed amendments to claims 43, 50, 51 and 59 of Application No. 09/972,178 for discussion during interview on November 6, 2002

43. (Amended) An electronic device which comprises a first electrode provided on an electronic component and a second electrode formed on a circuit board, the both electrodes being electrically connected with each other by means of a [solder] solder-containing portion, wherein an Sn-Bi alloy layer containing 1 to 5 wt% Bi is on the first electrode and the Sn-Bi alloy layer is in contact with [solder] solder-containing portion [of] from a Pb-free alloy, and the [solder] solder-containing portion is in contact with the second electrode.

50. (Amended) An electronic device which comprises a first electrode provided on an electronic component and a second electrode provided on a circuit board on which the electronic component is mounted, the both electrodes being bonded with each other by means of a solder, wherein an Sn-Bi alloy layer containing 1 to 5 wt% Bi is [adjacent] in contact with the first electrode as a surface layer, and the Sn-Bi alloy layer is in contact with [the solder] a solder bonding portion made [of] from Pb-free alloy, and the solder bonding portion is in contact with the second electrode.

51. (Amended) An electronic device which comprises an electronic component having a first electrode with an Sn-Bi alloy layer, a circuit board with a second electrode, and a bonding part [of] formed from a Pb-free solder which bonds the first electrode and the second electrode to each other, wherein the Sn-

Bi alloy layer contains 1 to 5 wt% Bi and is on the first electrode, and the [Pb-free solder] bonding part is in contact with the second electrode.

59. (Amended) An electronic device which comprises a semiconductor provided with a first electrode and a second electrode formed on a circuit board, the both electrodes being electrically connected with each other by means of a solder, wherein an Sn-Bi alloy layer containing 1 to 5 wt% Bi is [adjacent] in contact with the first electrode as a surface layer, and the Sn-Bi alloy layer is in contact with the solder bonding portion, made [of] from a Pb-free alloy, and the solder bonding portion is in contact with the second electrode.

Proposed amendments to claims 1, 12, 17 and 23 of Application No. 10/183,897 for discussion during interview on November 6, 2002

1. (Amended) A semiconductor device with a lead which is made from a lead frame, wherein the lead has [an] a layered structure thereon which consists of a single Sn-Bi alloy layer, comprising 1 to 5 wt% Bi, thereon.

12. (Amended) A semiconductor device with a lead which is made from a lead frame, wherein [an] a layered structure which consists of a single Sn-Bi alloy layer, which comprises from 1 to 5 wt% Bi, is formed on the lead.

17. (Amended) A semiconductor device with a lead which is made from a lead frame, wherein [an] a layered structure which consists of a single Sn-Bi alloy layer, which comprises from 1 to 5% Bi, is formed directly on the lead.

23. (Amended) A semiconductor device with a lead which is made from a lead frame, wherein an Sn-Bi alloy layer, which comprises from 1 to 5 wt% Bi, is formed directly on the lead as a surface layer.